



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625, U.S.A

T: 610-272-8000
F: 610-272-6759

www.electroscience.com

CERMET RESISTOR SYSTEM

PTC 2600-I SERIES

The PTC 2600-I Series of thermistor pastes is designed for making positive temperature coefficient thermistor films. Application where thermistors are required to be intimately bonded to the substrate such as temperature compensation of hybrid circuits and fast response sensors may be achieved with the PTC 2600-I Series. When used as temperature sensors, a linear response is obtained from ambient to temperatures in excess of 300°C with the advantage of reduced size and lower cost. Four values of sheet resistivity are available: 5 Ω /sq., 10 Ω /sq., 100 Ω /sq., and 1 k Ω /sq.

The 2600-I Series is designed to withstand high power dissipation and is ideally suited to the manufacturing of self limiting thick film heater elements for a wide range of consumer and industrial applications.

PASTE DATA

RHEOLOGY:	Thixotropic, screen printable paste
VISCOSITY: (Brookfield RVT, 10 rpm, ABZ spindle, 25.5°C±0.5°C)	200±30 Pa•s
SHELF LIFE:	6 months

PROCESSING

SCREEN MESH/EMULSION:	200/18 microns
LEVELING TIME: (20°C-25°C)	5-10 minutes
DRYING AT 125°C:	10-15 minutes
FIRING TEMPERATURE RANGE:	825°C-850°C (in air)
OPTIMUM (CALIBRATION):	850°C
TIME AT PEAK TEMPERATURE:	10 minutes

ESL Europe (KOP) PTC-2600-I 9211-C

ESL Affiliates

ESL Europe (Agmet Ltd) • 8 Commercial Road • Reading • Berkshire • England • RG2 0QZ • Tel: +44 (0) 118 918 2400 • Fax: +44 (0) 118 986 7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg. • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: +81-3-3864-8521 • Fax: +81-3-3864-9270 • Sales@ESL-Nippon.co.jp

ESL China • Room #1707, Tower A, City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 • Tel: +86-21-6237-0336 and 0337 • Fax: +86-21-6237-0338
ESLChina@eslshanghai.net

See Caution and Disclaimer on other side.

RATE OF ASCENT / DESCENT:	50°C-60°C/minute
SUBSTRATE FOR CALIBRATION:	96% alumina
RECOMMENDED TERMINATION:	9912-A
THINNER:	ESL 401

TYPICAL PROPERTIES

DRIED PRINT THICKNESS:

(on 96% alumina) 22.5 ± 2.5 µm

RESISTIVITY:	2650-I	5 Ω ±30%
	2611-I	10 Ω ±20%
	2612-I	100 Ω ±20%
	2613-I	1 kΩ ±10%

TCR:

(Measured on a
2 mm x 20 mm resistor)

2650-I	Hot and Cold sides	3400 ± 400 ppm/°C
2611-I	Hot and Cold sides	3000 ± 400 ppm/°C
2612-I	Hot and Cold sides	2200 ± 400 ppm/°C
2613-I	Hot and Cold sides	1600 ± 400 ppm/°C

VOLTAGE GRADIENT: > 25V/mm

ESL Europe (KOP) PTC-2600-I 9211-C

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.