

416 EAST CHURCH ROAD KING OF PRUSSIA, PA 19406-2625, U.S.A

F: 610-272-6759

T: 610-272-8000

www.electroscience.com

CATHODE PASTE

4421

RoHS Compliant* • For SOFC & Other Fuel Cells

ESL 4421 is a cathode composition that contains LSCF ($La_{0.8}Sr_{0.2}Fe_{0.8}Co_{0.2}Oxide$). It is a screen-printable or dispensable thick-film paste.

PASTE DATA

Rheology: Thixotropic, screen-printable paste

Viscosity:

(Brookfield RVT, 10 rpm, ABZ spindle, 25.5 ± 0.5 °C)

100 ± 50 Pa.s

Colour: Black

Shelf Life (20 - 25 °C): 6 months

PROCESSING

Levelling Time (at 20°C): 5 - 10 min

Drying Time (at 125°C): 10 - 15 min



ESL Europe (KOP) 4421 0607-New

*None of the six substances referred to in the RoHS Directive (2002/95/EC) are used in the formulation of this product.

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.